

PAPER KAOLIN

PRODUCT CHARACTERISTICS	FILLER		COATING	
	KX 0	KX 1	FDK 1	FDK 2
WHITENESS, %	86.0+/-1.0	84.0+/-1.0	86.0+/-1.0	84.0+/-1.0
YELLOWNESS, %	6.3+/-0.7	7.3+/-0.7	5.5+/-0.5	6.5+/-0.5
CONTENT OF LESS 2 MICR. PARTICLES,%	min.67.0	min.65.0	min.88.0	min.86.0
CONTENT OF LESS 5 MICR. PARTICLES,%	min.85.0	min.83.0	min.97.0	min.97.0
CONTENT OF OVER 10 MICR. PARTICLES,%	max.2.0	max.3.0	max.1.0	max.1.5
WET RESIDUE ON SIEVE 45 MICR.,%	max.0.03	max.0.05	max.0.02	max.0.03
ABRASION, mg	max.17.0	max.20.0	max.6.0	max.8.5
PH	6.0+/-0.5	6.0+/-0.5	6.0+/-0.5	6.0+/-0.5
SPECIFIC SURFACE, g/cm2	17+/-1.0	17+/-1.0	19+/-1.0	19+/-1.0
BULK DENSITY, g/cm3	0.9	0.9	0.9	0.9
HUMIDITY, %	12.0+/-2.0	12.0+/-2.0	12.0+/-2.0	12.0+/-2.0