

	PK 063	PK 08	PK 1.0	0.6-2	1-3	3-5
Granulometry, %						
+ 2.000 mm		0	max. 10			
- 2.000 mm + 1.600 mm	0	max. 10	15 - 25			
- 1.600 mm + 1.000 mm	0-10	15-30	30 - 50			
- 1.000 mm + 0.800 mm	10-30	25-50	20 - 35			
- 0.800 mm + 0.630 mm	25-45	15-35	max. 15			
- 0.630 mm + 0.400 mm	20-40	max. 10				
- 0.400 mm	max. 10					
d50%	0.63-0.8	0.8-1.0	1.0 - 1.6			
Humidity, %	max. 1.0	max. 1.0	max. 1.0			
	PK 063	PK 08	PK 1.0	0.6-2	1-3	3-5
Granulometry, %						
+ 5.000 mm				0	0	
-5.000 mm + 3.150 mm				max. 1	max. 1	
-3.150 mm + 2.500 mm				max. 2	max. 5	
- 2.500 mm + 2.000 mm				max. 3	max. 5	
- 2.000 mm + 1.600 mm				5-15	max. 5	
- 1.600 mm + 1.000 mm				20-60	55-75	
- 1.000 mm + 0.800 mm				15-30	10-25	
- 0.800 mm + 0.630 mm				5-20	2-5	
- 0.630 mm + 0.400 mm				2-10	0-5	
- 0.400 mm				0-2		
Humidity, %				max. 1.0	max. 1.0	
	PK 063	PK 08	PK 1.0	0.6-2	1-3	3-5
Granulometry, %						
+ 6.000 mm						max. 1
-6.000 mm + 5,600 mm						max. 8
-5.600 mm + 3,150 mm						80-90
-3.150 mm + 2,000 mm						max. 8
-2.000 mm						max. 2
Humidity, %						max. 1.0
Chemical Composition, %						
SiO ₂	min. 98.5	min. 98.5	min. 98.5	min. 94.0	min. 94.0	min. 97.7
Al ₂ O ₃	max. 0.5	max. 0.5	max. 0.5	max. 3.0	max. 3.0	max. 0.65
Fe ₂ O ₃	max. 0.15	max. 0.15	max. 0.15	max. 0.15	max. 0.15	max. 0.10
TiO ₂	max. 0.10	max. 0.10	max. 0.10	max. 0.10	max. 0.10	
CaO+MgO+ Na ₂ O+ K ₂ O	max. 1.0	max. 1.0	max. 1.0	max. 2.0	max. 2.0	max. 0.85